



FullBand® Low Water Peak Single-mode Fibre

Description

NEXTRA FullBand® low water peak dispersion unshifted Single-mode fibre is designed specially for optical transmission systems operating over the entire wavelength window from 1260 nm to 1625 nm. By suppressing the water peak that occurs near 1385 nm in conventional single mode fibre due to hydroxyl (OH) ions absorption, FullBand® fibre is able to open E-band (1360-1460 nm) for operation, and consequently provides 100 nm more usable wavelengths.

Application

Thanks to its broad usable optical spectrum and outstanding optical performance, FullBand® fibre is the optimum choice that supports various applications such as Ethernet, Internet Protocol (IP), Asynchronous Transfer Mode (ATM), Synchronous Optical Network (SONET) and Wavelength Division Multiplexing (WDM). FullBand® fibre provides more bandwidth for backbone, metropolitan area and access networks.

NEXTRA FullBand® fibre complies with or exceeds the ITU-T Recommendation G.652.D and the IEC 60793-2-50 type B1.3 Optical Fibre Specification.

NEXTRA tightens many parameters of fibre products so as to offer more conveniences to customers.

NEXTRA fibres are manufactured using the advanced Plasma Activated Chemical Vapor Deposition (PCVD) process. Because of the inherent advantages of the process, NEXTRA fibres show extremely refined refractive index (RI) profile control, excellent geometrical performance, low attenuation, etc.

Characteristics

Due to the process innovation and technical breakthrough made on the basis of the conventional Single-mode fibre.

NEXTRA FullBand® low water peak Single-mode fibre has the following characteristics:

- Designed for operation over the full optical spectrum from 1260-1625 nm, which provides 50% more usable wavelengths and hence the transmission capacity is increased
- Outstanding optical performance supporting high-speed transmission technologies such as DWDM and CWDM
- Being compatible with existing 1310 nm equipment
- Good protection and excellent strip force stability
- Accurate geometrical parameters that insure low splicing loss and high splicing efficiency

Characteristics	Conditions	Specified Values	Units
Optical Characteristics			
Attenuation	1310 nm	≤0.34	[dB/km]
	1383 nm	≤0.34	[dB/km]
	1550 nm	≤0.20	[dB/km]
	1625 nm	≤0.23	[dB/km]
Attenuation vs. Wavelength Max. α difference	1285-1330 nm	≤0.03	[dB/km]
	1525-1575 nm	≤0.02	[dB/km]
Dispersion coefficient	1285-1340 nm	≥-3.4 ≤3.4	[ps/(nm · km)]
	1550 nm	≤18	[ps/(nm · km)]
	1625 nm	≤22	[ps/(nm · km)]
Zero dispersion wavelength		1312±12	[nm]
Zero dispersion slope		≤0.091	[ps/(nm ² · km)]
Typical value		0.086	[ps/(nm ² · km)]
PMD			
Maximum Individual Fibre		≤0.1	[ps/√km]
Link Design Value (M=20,Q=0.01%)		≤0.06	[ps/√km]
Typical value		0.04	[ps/√km]
Cable cutoff wavelength λ_c		≤1260	[nm]
Mode field diameter (MFD)	1310 nm	8.7-9.5	[μm]
	1550 nm	9.9-10.9	[μm]
Effective group index of refraction (Neff)	1310 nm	1.466	
	1550 nm	1.467	
Point discontinuities	1310 nm	≤0.05	[dB]
	1550 nm	≤0.05	[dB]
Geometrical Characteristics			
Cladding diameter		125.0±0.7	[μm]
Cladding non-circularity		≤10	[%]
Coating diameter		245 ±7	[μm]
Coating-cladding concentricity error		≤12.0	[μm]
Coating non-circularity		≤6.0	[%]
Core-cladding concentricity error		≤0.6	[μm]
Curl (radius)		≥4	[m]
Delivery length		2.1 to 50.4	[km/reel]
Environmental Characteristics (1310 nm, 1550 nm & 1625 nm)			
Temperature dependence			
Induced attenuation at	-60°C to +85°C	≤0.05	[dB/km]
Temperature-humidity cycling			
Induced attenuation at	-10°C to+85°C, 98% RH	≤0.05	[dB/km]
Watersoak dependence			
Induced attenuation at	23°C, for 30 days	≤0.05	[dB/km]
Damp heat dependence			
Induced attenuation at	85° and 85% RH, for 30 days	≤0.05	[dB/km]
Dry heat aging at	85°C	≤0.05	[dB/km]
Mechanical Specification			
Proof test		≥9.0	[N]
		≥1.0	[%]
		≥100	[kpsi]
Macro-bend induced attenuation			
1 turn around a mandrel of 32 mm diameter	1550 nm	≤0.05	[dB]
100 turns around a mandrel of 50 mm diameter	1310 nm & 1550 nm	≤0.05	[dB]
100 turns around a mandrel of 60 mm diameter	1625 nm	≤0.05	[dB]
Coating strip force	typical average force	1.5	[N]
	peak force	≥1.3 ≤8.9	[N]
Dynamic stress corrosion susceptibility parameter n _d		≥20	